

PRODUCT SPECIFICATION SHEET

BELZONA 4131

FN10077



General Information

Product Description:
A two-component system consisting of high molecular weight polymers and oligomers incorporated with an aggregate mix. Once fully cured, the system provides excellent protection to concrete from the effects of impact, abrasion, and chemical attack.

Application Areas:
When mixed and applied as detailed in the Belzona Instructions for Use (IFU), the system is ideally suited for application to the following:

- Floors	- Walls	- Aisles
- Ramps	- Stairways	- Warehouse loading bays
- Lifts	- Chemical storage areas	- Machinery/production areas

Application Information

Working Life Will vary according to temperature. At 77°F (25°C), use all mixed material within 30 minutes.	Base Component Appearance Color Density	Damp sand Gray 2.3 - 2.5 g/cm³
Coverage Rates Each 20 kg unit applied at film thickness of ¼ inch (6 mm) will cover 15 ft² (1.4 m²).	Solidifier Component Appearance Color Density	Clear liquid Light or Amber 0.99 g/cm³
Cure Time Allow to solidify for the times shown in the Belzona IFU before subjecting it to the conditions indicated.	Mixed Properties Mixing Ratio by Weight (Base: Solidifier)	30: 1
Volume Capacity 524 in³ (8590 cm³) per 20 kg unit.		
<i>The above application information serves as introductory guide only. For full application details including the recommended application procedure/technique, refer to the Belzona IFU which is enclosed with each packaged product.</i>		

PRODUCT SPECIFICATION SHEET

BELZONA 4131

FN10077



Abrasion

Taber
When tested in accordance with ASTM D4060 with a 1-kg load, typical loss per 1,000 cycles is:

Wet (H10 wheels) 685 mm³

Adhesion

Tensile Shear
The tensile shear adhesion to steel of the polymeric binder, when tested in accordance with ASTM D1002 is typically 2,400 psi (169 kgf/cm²)

PosiTest dolly pull-off (ASTM D4541)

Dry concrete	600 psi (4.14 MPa)*
Wet concrete	425 psi (2.93 MPa)*

* Cohesive failure of substrate

Chemical Resistance

Demonstrates excellent chemical resistance to most inorganic acids up to 10% concentration and alkalis up to 20% concentration. Is resistant to salt solutions, hydrocarbons, and mineral oils.

* For a more detailed description of chemical resistance properties, refer to relevant Chemical Resistance chart.

Compressive Properties

Compressive Strength
When tested in accordance with ASTM D695 is typically 10,500 psi (72.39 MPa)

Flexural Properties

Flexural Strength
When tested to ASTM D790 is typically 4,600 psi (31.71 MPa)

Heat Resistance

Heat Distortion Temperature (HDT)
The heat distortion temperature when tested to ASTM D648 is typically 100 °F (38 °C).

Heat Resistance
For many typical applications, the product is thermally stable to 300 °F (150 °C) dry and 140 °F (60 °C) wet, and down to -40 °F (-40 °C).

Impact Properties

Impact Strength
The Izod impact strength when tested to ASTM D256 is typically 0.35 ft.lb. /in. (19 J/m).

Shelf Life

Separate base and solidifier components shall have a shelf life of 5 years from date of manufacture when stored in their original unopened containers between 41 °F (5 °C) and 86°F (30°C).

PRODUCT SPECIFICATION SHEET

BELZONA 4131

FN10077



Warranty

Belzona guarantees this product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona Information for Use leaflet. Belzona further guarantees that all its products are carefully manufactured to ensure the highest quality possible and tested strictly in accordance with universally recognized standards (ASTM, ANSI, BS, DIN, ISO etc.). Since Belzona has no control over the use of the product described herein, no warranty for any application can be given.

Availability and Cost

Belzona 4131 is available from a network of Belzona Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona Distributor in your area.

Manufacturer/Supplier

Belzona Polymerics Ltd.
Claro Road, Harrogate,
HG1 4DS, UK

Belzona Inc.
14300 N.W. 60th Ave,
Miami Lakes, FL, USA, 33014

Health and Safety

Prior to using this material, please consult the relevant Material Safety Data Sheets.

Technical Service

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development, and quality control laboratories.

The technical data contained herein is based on the results of long-term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2024 Belzona International Limited. Belzona® is a registered trademark.

*Belzona products are
manufactured under an
ISO 9001 Registered
Quality Management System*

