Coating for the Protection of Process Equipment Operating at Elevated Temperatures





Belzona 1593 is a high-temperature coating suitable for equipment operating in continuous immersion in aqueous and hydrocarbon systems at temperatures up to 160°C (320°F). It provides excellent long-term corrosion resistance and withstands a wide range of chemicals.

This material has a 24-hour overcoat window allowing applications to be effectively and quickly completed, with downtime kept to a minimum. Its ambient temperature curing mechanism with full in-service cure allows for a rapid turnaround and return to service.

This solvent-free material is proven to outperform conventional Vinyl Ester Glass Flake (VEGF) coatings in terms of mechanical strength and adhesion, and exhibits reduced shrinkage and VOC emissions.

This high-performance coating is also resistant to steam-out processes up to 250°C (482°F) and rapid depressurisation.

| TECHNICAL DATA | Mixing ratio (base:solidifier) | 11:1 by weight | 5.6:1 by volume | | | |
|----------------|-------------------------------------|---|--|--|--|--|
| | Working life | 45 minutes at 20°C (68°F) | | | | |
| | Shelf life | 3 years | | | | |
| | Dry heat resistance | 220°C (428°F) | | | | |
| | Adhesion (tensile shear) mild steel | 20 MPa (2,900 psi) at 20°C (68°F) cure | 12.3 MPa (1,790 psi) at 160°C (320°F) cure | | | |
| | Compressive strength | 57.1 MPa (8,280 psi) at 20°C (68°F) cure | | 34.6 MPa (5,010 psi) at 160°C (320°F) cure | | |
| | Coverage rate | 1.1 m² (11.84 ft²) /kg at 500 microns (20 mils) | | | | |
| | Heat distortion temperature | 49°C (120°F) at 20°C (68°F) cure | 168°C (334°F) at 100°C (212°F) cure | 234°C (453°F) at 160°C (320°F) cure | | |
| | Abrasion resistance | H10 - 1,042 mm³ wet | CS17 - 17.4 mm³ dry | | | |
| | | | | | | |

| | Temperature | 10°C (50°F) | 20°C (68°F) | 30°C (85°F) | 40°C (105°F) |
|------------|--|-------------|-------------|-------------|--------------|
| CURE TIMES | Time until inspection | 42 hours | 20 hours | 8 hours | 4 hours |
| | Time until full service | 10 days | 72 hours | 30 hours | 9 hours |
| | Time until dry post cure (if required) | 42 hours | 20 hours | 8 hours | 4 hours |
| | Time until wet post cure (if required) | 4 days | 40 hours | 14 hours | 7 hours |

^{*}Please visit the product page and consult the Product Specification Sheet (PSS) and Instructions for Use (IFU) for the latest technical data.



VERY HIGH HEAT DISTORTION TEMPERATURE



EROSION-CORROSION RESISTANT



HIGH ADHESION



REDUCED DOWNTIME

BELZONA 1593



Key Benefits:

Simple and safe to use

Belzona 1593 is easy to mix and apply without specialist tools. This coating is safe to apply in confined spaces, reducing health and safety risks.

• Excellent resistance to corrosion and chemicals

This coating provides long-term corrosion resistance even under immersed conditions at high temperatures.


• Immersed, high temperature operation


The material is designed to operate under immersed conditions in aqueous and hydrocarbon systems up to 160°C (320°F)

Minimised downtime

Downtime is reduced due to Belzona 1593's post-cure mechanism activated at service temperatures.

Test Data:





Application Areas:

- Boiler vessels
- Condensers
- Heat exchangers
- Flare knock-out vessels and evaporators
- Separators





The light colours of Belzona 1593 allow easy visual inspection in vessels.

For more information, please contact your local Belzona representative:

QUALITY PRODUCTS - TECHNICAL SUPPORT

Belzona products are manufactured under an ISO 9001 Registered Quality Management System.

Belzona has a global distribution network of over 140 Distributors operating in 120 countries. Local support is provided by a trained Technical Consultant who will diagnose the problem, recommend the solution and provide 24-hour, on-site application supervision and advice.